

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **08107068 A**

(43) Date of publication of application: **23.04.96**

(51) Int. Cl

H01L 21/203

H01L 21/20

(21) Application number: **06238800**

(71) Applicant: **NEC CORP**

(22) Date of filing: **03.10.94**

(72) Inventor: **KAWANO MASAYA**

(54) **GROWTH METHOD OF CDTE ON SI SUBSTRATE BY MBE METHOD** COPYRIGHT: (C)1996,JPO

(57) Abstract:

PURPOSE: To make high quality CdTe crystal grow on an Si substrate by an MBE method regardless of the construction of a growth apparatus and a cleaning method.

CONSTITUTION: An Si substrate is washed and introduced into a growth apparatus and held in an extra-high vacuum at 500°C for several hours. After that, the substrate is held at 850°C for 5 minutes as the cleaning 1 of Si for removing a surface oxide film. Then the substrate temperature is lowered to 750°C to irradiate it with As+Cd 2 for 5 minutes. Then irradiation with As is discontinued and, while irradiated with Cd only 3, the substrate temperature is lowered. After the substrate temperature is lowered to 180°C, the (1st) growth 4 of CdTe is started. 1 minute after the start of the CdTe growth, the irradiation 3 with Cd is discontinued. After the (1st) growth 4 of CdTe is continued for 30 minutes, the substrate is held (anneal 4) at 340°C for 10 minutes and the (2nd) growth 5 of CdTe is started again at 290°C.

